

APPLICANT: LI PENG ENTERPRISE CO., LTD.  
6/F., NO. 162,  
SUNG CHIANG RD.,  
TAIPEI,  
TAIWAN, R. O. C.

DATE: MAY 25, 2006

SAMPLE DESCRIPTION :

ONE (1) PIECE OF SUBMITTED SAMPLE SAID TO 100% POLYESTER WOVEN FABRIC IN TAN FOR CURTAIN USE.

APPLICANT'S PROVIDED CARE INSTRUCTION/LABEL : -

DATE RECEIVED/DATE TEST STARTED : MAY 23, 2006


STANDARD : -  
STYLE/ARTICLE NO. : S1833Z  
ORDER NO. : -  
BUYER'S NAME : -  
MANUFACTURER'S NAME : -  
AGENT'S NAME : -  
REF. : -

CONCLUSION:

THE SUBMITTED SAMPLE MEETS THE REQUIREMENTS STATED IN NATIONAL FIRE PROTECTION ASSOCIATION NO. 701-1989 SMALL SCALE FOR FIRE TESTS OF FLAM RESISTANT TEXTILES & FILMS.

REMARK : FABRIC WEIGHT : 7.3 OZ/YD<sup>2</sup>

AUTHORIZED BY:  
ON BEHALF OF INTERTEK TESTING SERVICES  
TAIWAN LIMITED



CAROL PENG  
DIRECTOR  
TEXTILE AND FOOTWEAR DIVISION

TESTS CONDUCTED (AS REQUESTED BY THE APPLICANT)

- 1 FIRE TEST FOR FLAME - RESISTANT TEXTILES AND FILMS (NFPA 701-1989 SMALL SCALE TEST) :

REQUIREMENTS:

1. MATERIAL SHALL NOT CONTINUE FLAMING FOR MORE THAN TWO SECONDS AFTER THE TEST FLAME IS REMOVED FROM CONTACT WITH THE SPECIMEN.
2. CHAR LENGTH - 5.5 INCHES MAXIMUM FOR ANY SPECIMEN  
- 4.5 INCHES MAXIMUM FOR AVERAGE OF 10 SPECIMENS
3. PORTIONS OR RESIDUES OF TEXTILE OR FILMS WHICH BREAK OR DRIP FROM THE TEST SPECIMEN SHALL NOT CONTINUE TO FLAME AFTER THEY REACH THE FLOOR OF THE TEST.

TEST RESULTS:

SPECIMEN	<u>CHAR LENGTH</u> (INCH)	<u>AFTER FLAME TIME</u> (SECOND)	<u>RESIDUAL FLAME TIME</u> (SECOND)
1.	3.6	NIL	NIL
2.	3.5	NIL	NIL
3.	3.5	NIL	NIL
4.	3.6	NIL	NIL
5.	3.4	NIL	NIL
6.	3.9	NIL	NIL
7.	2.8	NIL	NIL
8.	2.6	NIL	NIL
9.	4.8	NIL	NIL
10.	<u>4.0</u>	NIL	NIL
AVERAGE.	3.6		

REMARK : FABRIC WEIGHT : 7.3 OZ/YD<sup>2</sup>

---